

SpECtite PUFlex

ONE-COMPONENT, PU BASED HIGH ELASTIC POLYURETHANE WATERPROOFING MEMBRANE

DESCRIPTION

SpECtite PUFlex is a one-component high build polyurethane polymer based elastomeric coating. The dry film possesses superior physical properties. The dry membrane is water tight, seamless, durable, tough, highly flexible and weather resistant.

SpECtite PUFlex utilises the latest in polyurethane technology to perform as a UV resistant membrane with excellent durability even in harsh/hot Middle East climatic conditions.

TYPICAL USES

SpECtite PUFlex may be used for the following situations:

- Waterproofing of roofs (asbestos, cement tile terrazzo and concrete)
- Waterproofing of domes, arches, terraces, balconies, sunshades & parapet walls
- Wet area, i.e. under tiles in bathroom, kitchen and shower areas, swimming pools
- Waterproofing over old refurbished roof

ADVANTAGES

- One-component ready to use, light weight compared to conventional roof system
- Formulated to withstand harsh Middle East climate
- Non-flammable and non-hazardous
- Highly elastic and UV resistant
- High crack building capability

TECHNICAL DATA

Appearance	Thixotropic coating
Full cure	7 days
Solids content	65±3%
Density (ASTM D1475)	1350±50 kg/m ³

Elongation

(ASTM D882) 500±50%

Crack Bridgeability

(ASTM C836) 3.0±0.5mm

Tear resistance

(ASTM D624) 6±2 kN/m

Shore A Hardness

(ASTM D2240) 45±5

Service temperature -5 °C - 90 °C

APPLICATION

Surface Preparation

Surfaces must be dry and free from oil, dust, dirt, grease and loosing materials. The substrate should be firm, in case of gaps and cracks fill with suitable polysulphide sealant and ensure the surface is level.

Substrate Priming

For most situations, the substrate should be primed with **SpECtite PUFlex Primer**. **SpECtite PUFlex** can be applied as soon as the primer becomes tack-free.



Application

Stir well before use. Do not apply if rain is expected within 24 hours. Apply the material using brush or roller. A second coat is applied at right angle to the first coat, after the first coat is dry. It is recommended to apply two coats of **SpECtite PUFlex** to get a thickness of 1mm. Multiple coats can be applied to achieve higher thickness. Embed fiber mesh around

all corner joints, fillets, pipe penetration, pipes, over cracks, drains and where substantial movement is anticipated. Lay fibre mesh in the wet first coat before the application of subsequent coats.

Curing

It requires 24 hours to dry in between 2 coats and 48 hours curing is adequate for foot traffic. Low temperature and high humidity will slow down the curing process. 7 days are required for full cure. In case of expected rains, do not apply **SpECTite PUFlex**. Ensure curing is complete before laying thermal insulation board mechanical protection and other coverings.

APPLICATION TEMPERATURE RANGE

5 °C to 50 °C

EQUIPMENT CLEANING

SpECTite PUFlex should be cleaned from equipment using soap and water immediately after application.

PACKAGING & YIELD

SpECTite PUFlex is supplied in 20 litres pail with a coverage rate of 1 m²/litre/2 coats at 1mm wft.

SpECTite PUFlex Primer is supplied in 20 litres pail with a coverage rate of 8-10 m²/litre.

STORAGE & SHELF LIFE

When stored in a cool environment in original unopened containers, the material has a shelf life of 12 months.

LIMITATIONS

Do not use **SpECTite PUFlex** in poor drainage areas that will be constantly underwater. It applies only in case it is exposed without any protection layer.

PROTECTION FROM MECHANICAL DAMAGE

The cured membrane could be damaged by sharp objects and should be protected against damage and site abuse by other trades. Terminates the edge of the coatings securely to avoid peeling-off. Protect the coating with cement screed in heavy traffic areas. This should be done after 48 hours of curing.

HEALTH AND SAFETY

Eyes should be protected from splashes by wearing goggles. In the event of contact with your eyes irrigate immediately with clean water and seek medical attention.

Skin contact should be avoided by wearing protective gloves and outer clothing. The product may be removed from the skin when wet by water and soap, and when dry by using a proprietary hand cleaner.

If ingested, seek medical attention immediately.

FLAMMABILITY

SpECTite PUFlex is a non-flammable and non-hazardous in normal use.

Issue 10: 04/2021

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: info@spec.ae

www.spec.ae